Original Comfort
Technical data.

BERRY ALLOC

03/2025

	contains	m²	t²	weight
1 pack Original Comfort	8 planks	1,9119 m²	20,57 t²	16,7 kg
1 pallet Original Comfort	36 packs	68,83 m²	740,86 t²	622 kg

product specifications

Dimensions	1207 x 198 mm
Total thickness	11 mm (9 + 2)
Bevels	0/2/4
Loc System	HighTec Loc
Level of use according to European standard EN10874	23 heavy domestic use
	34 heavy commercial use
Residential warranty	lifetime
Commercial warranty	10 years

Warranty conditions on www.berryalloc.com.

composition

Surface layer	AC6, High pressure laminate, impregnated with melamine and phenol resin
Substrate	Water resistant High Density Fiberboard (+950 kg/m³)
Backing	Engineered balancing foil
Underlay material	BerryAlloc SilentSystem, attached to the reversed side of the board

test results

Abrasion resistance	EN13329	AC6 (IP≥8500)
Impact resistance	EN13329	small ball : ≥ 15 N - big ball ≥ 1600 mm)
Thickness swelling	ISO 24336	7 % (requirement ≤ 8 %)
Water resistance	ISO 4760	lifetime (according to warranty conditions)
Fire resistance	EN13501-1	Bfl-S1
Formaldehyde emission	EN717-1	E1
Slip resistance	EN13893	DS
Density	EN323	950 kg/m³
Resistance to staining	EN438.2.26	5 (groups 1+2) ; 4 (group 3)
Effect of a furniture leg	EN424	no damage (foot type 0)
Effect of a castor chair	EN425	No damage or visible change in appearance at 25.000 rev. with hard wheels (type H)
Thermal resistance with integrated underlay	ISO 8302 (EN12664 / EN12667)	0,072 m²K/W – Suitable for floor heating/cooling. Detailed instructions on www.berryalloc.com.

EN 14041
CE 15 DOP 110-OR3415-1
UKCA 22 DOC UK 110-OR3422-1
Berryalloc NV
Industrielaan 100
8930 Menen, Belgium
NB 1161
Laminate floor covering for use within building
www.berryalloc.com

PEFC Certified
laminate flooring from sustainably managed forests and controlled sources
PEFC/03-31-89
www.pefc.be

ÉMISSIONS DANS L'AIR INTÉRIEUR*
A
A+ A B C
*Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).

23
34

EMISSION CLASS FOR BUILDING MATERIAL · RTS ·
M1

high pressure floors.

www.berryalloc.com

Original Comfort
Technical data.

BERRY ALLOC

03/2025

What is a High Pressure Floor made of?



1. AC6 overlay/Class 34
2. Impregnated **decor paper**
3. Impregnated Kraft paper (2 layers)
4. Water resistant HDF board
5. Counterbalance paper
6. SilentSystem
7. HighTec Loc

high pressure floors.