Technical Data Sheet

Design flooring **555 Wooden Styles Click Herringbone**

Click-type design floor covering



Article number(s):	701H | 702H | 703H | 704H | 705H | 706H

Material / structure	
Structure	Transparent wear layer incl. PU coating LVT SPC core LVT Integrated impact sound installation IXPE
Surface appearance	Wide range of wood looks with chamfered edges
Surface treatment	PU coating with synchronous pore
Connection system	ProConnect laying system
Laying options	Floating installation

04|2025

Information subject to technical modification and error. All previous data sheets are no longer valid on publication of this edition.

W. & L. Jordan GmbH | Horst-Dieter-Jordan-Straße 7-10 | D-34134 Kassel | info@joka.de | www.joka.de
INKU Jordan GmbH & Co. KG | IZ-NÖ Süd | Straße 3 | A-2355 Wiener Neudorf | info@inku.at | www.inku.at

Technical Data Sheet

Design flooring **555 Wooden Styles Click Herringbone**

Dimensions and tolerance values in accordance with DIN EN ISO 10582. Dimension characteristics and permissible deviations in dimensions specified in the factory have been given in accordance with the type of elements for elastic floor coverings.

Dimensions of the individual element

Dimension	Tolerances
Thickness: 7.0 mm	
Length: 750.0 mm	
Width: 150.0 mm	
Thickness of the wear layer 0.55 mm	
Permissible deviation in width	≤ 0.10 % up to maximum 0.5 mm
Permissible deviation in perpendicularity	≤ 400 mm ≤ 0.25 mm > 400 mm ≤ 0.35 mm
Permissible deviation in straightness	≤ 400 mm ≤ 0.25 mm > 400 mm ≤ 0.35 mm
Permissible deviation in length	≤ 0.15 % up to maximum 0.5 mm
Permissible deviation in thickness of the element	± 0.15 mm
Change in dimension following effect of heat	≤ 0.15 %
Warping following effect of heat	≤ 1.0 mm

Product characteristics

Performance class	23/33/42
Fire behaviour	B_{fl} s1
Slip resistance	R10 / DS
Electrostatic behaviour	≤ 2 kV
Colour fastness	> Level 6
Castor chair test	Suitable chair caster type W
Residual indentation behaviour	< 0.05 mm
Chemical resistance	Resistant*
Thermal resistance	0.04 (m² x K) / W suitable for hot water underfloor heating
Pentachlorophenol content	Not detectable
Formaldehyde content	E1
Phthalate content	Phthalate-free
Weight per unit area	10,950 g/m²
Impact noise enhancement	approx. 21 dB

*Resistance depends on concentration and exposure time. In the event of increased exposure to oils, greases, acids, lyes and other aggressive chemicals, the manufacturer must be consulted.

Information subject to technical modification and error. All previous data sheets are no longer valid on publication of this edition.

W. & L. Jordan GmbH | Horst-Dieter-Jordan-Straße 7-10 | D-34134 Kassel | info@joka.de | www.joka.de
INKU Jordan GmbH & Co. KG | IZ-NÖ Süd | Straße 3 | A-2355 Wiener Neudorf | info@inku.at | www.inku.at

JOKA® Natürlich schöne Räume

INKU

Technical Data Sheet

Design flooring **555 Wooden Styles Click Herringbone**

Packaging	
Contents (area) per pack	1.575 m²
Contents per pallet	132.3 m²
Number of elements per pack	14
Packs per pallet	84

General product data	
DoP number	LVTDESF7

All samples, brochures and photos are only provided in order to give you rough idea and are not binding. Both age and exposure to sunlight have an impact on the natural changes in colour of printed finishes. The colours of the original may vary from the way they look in print media or on a screen. At the time of delivery, the product may therefore show clear differences from the material sample provided. Only the technical data sheet, which you can find at www.jordanshop.de, is relevant with regard to specific product properties.



04|2025

Information subject to technical modification and error. All previous data sheets are no longer valid on publication of this edition.

W. & L. Jordan GmbH | Horst-Dieter-Jordan-Straße 7-10 | D-34134 Kassel | info@joka.de | www.joka.de
INKU Jordan GmbH & Co. KG | IZ-NÖ Süd | Straße 3 | A-2355 Wiener Neudorf | info@inku.at | www.inku.at