

TECHNICAL DATA SHEET

Edition 06/2026

DIMENSIONS

FORMAT		BLOOM [AVMPU(-)] Medium Plank	CIRO [AVHBU(-)] Herringbone	ILLUME [AVMTU(-)] Medium Tile
Width	EN 17539:2021-08	209 mm	126 mm	428 mm
Length	EN 17539:2021-08	1494 mm	630 mm	856 mm
Number of panels per pack		6	10	6
m² per pack		1,873 m²	0,794 m²	2,198 m²
Weight per pack		15,7 kg	6,7 kg	18,4 kg
Tongue and groove		Uniclic® connection	Unizip® connection	Uniclic® connection
Total mass per unit area	EN ISO 23997:2012-02	8241 g/m²		
Total thickness	EN 17539:2021-08	6 mm (= 5+1 mm attached underlay)		
Finishing		Advanced PU -Top coating with Scratch & Stain Guard technology		
Bevels		Genuine		

PANEL BUILD-UP



- 1 Top lacquer
- 2 PVC járólaprteg
- 3 PVC printfilm
- 4 PVC soft layer
- 5 PVC backing with 2 glass fibers
- 6 Pad: 1 mm crosslinked polyethylene underlay

FACTORY WARRANTY

	METHOD	PARAMETERS	VALUES
Usage class	EN ISO 10874 / EN 16511:2023-05	Class	23 - 33
Product norm	EN 16511:2023-05		
UPEC (FR)	Bloom & Illume	Document Technique d'Application n° 12/24-1829_V1 - http://evaluation.cstb.fr	U ₃ P ₃ E ₂ C ₂
CE	EN 14041:2004+AC:2005+AC:2006	Notified body	NB 0493 - Centexbel
UKCA	EN 14041:2004+AC:2005+AC:2006	Approved body	AB 8515 - Centexbel International Ltd.
Warranty	Residential use	See warranty conditions	Lifetime
	Commercial use	See warranty conditions	5 years - on request up to 15 years

GENERAL DATA

	METHOD	PARAMETERS	NORM REQUIREMENTS	QUICK-STEP VALUES
Squareness & straightness	EN 17539:2021-08		q _{max} ≤ 0,20 mm s _{max} ≤ 0,30 mm/m	q _{max} ≤ 0,20 mm s _{max} ≤ 0,30 mm/m
Light fastness	EN ISO 105-B02:2014-08	Blue reference	Class ≥ 6	Class > 7
Dimensional stability	EN ISO 23999:2021-11	6 hrs at 80°C	≤ 0,15 %	≤ 0,15 %
Curling	EN ISO 23999:2021-11		≤ 2 mm	Average production result: ≤ 1 mm
Wear resistance	ISO 24338:2022-03, Procedure B		≥ 5000 cycles	Average production result: ≥ 7000 cycles
Impact resistance	EN 13329:2006+A1:2008-08, Annex F		≥ 1600 mm	Average production result: ≥ 1800 mm
Scratch resistance	EN 16094:2021-06, method A and B		ΔR' ≤ 1,5 (60°)	ΔR' < 1 MSR-B1
Castor chairs	EN ISO 4918:2021-03	25000 cycles		No delamination, no disturbance
Displacement of furniture feet	EN ISO 16581:2019-06	Foot 0,1 mm / 32 kg		No visible damage
Residual indentation	EN ISO 24343-1:2012-01		≤ 0,2 mm	Average production result: ≤ 0,05 mm
Resistance against staining	EN 438-2:2016+A1:2018-12	Acetone - Coffee - NaOH - H2O2 - Shoe Polish		Grade 5 (No change)
Swelling	ISO 24336:2005-03		≤ 18%	No swelling
Locking strength	ISO 24334:2019-07	F _{max} long side F _{max} short side	≥ 1,0 kN/m ≥ 1,5 kN/m	≥ 1,0 kN/m ≥ 1,5 kN/m
Water Resistance	ISO 4760:2022-05, Annex D	Joint leakage		No leakage
Acoustic insulation	DIN EN ISO 717-2:2021-05	Impact sound reduction		ΔL _w = 21 dB ΔL _{fin} = 10 dB
Floor heating		Appropriate for all standard heating systems IN cement subfloors. Limited application with heating films and alternatives. Max contact temp ≤ 27°C. See separate installation instructions.		

ENVIRONMENT, SAFETY & HEALTH

	METHOD	PARAMETERS	NORM REQUIREMENTS	QUICK-STEP VALUES
EPD				
AFFSET				A+
Floorscore				SCS-FS-09272
Finnish Building Emission				M1: Very low emission, odorless
Formaldehyde emission	EN 717-1:2004-10	No added formaldehyde in production	E1 ($\leq 0,124 \text{ mg/m}^3$)	< Detection limit
Indoor Air Comfort Gold				IACG-543-01-02-2025
TVOC 28 days	ISO 16000 part 9-6	AgBB requirement after 28 days	$<1000 \text{ } \mu\text{g/m}^3$	$< 20 \text{ } \mu\text{g/m}^3$
Fire classification	EN 13501-1:2018			Bfl-s1
Thermal resistance	EN 12667:2001-01			$0,035 \text{ m}^2 \text{ K/W}$
Slip resistance	EN 13893:2002-11		$\mu \geq 0,30$	DS
	EN 16165:2021-10 Annex B			R10
	BS EN 16165:2021 Annex C (UKSRG)	Wet		Low slip potential (PTV ₉₆ ≥ 36)
		Dry		Low slip potential (PTV ₉₆ ≥ 36)
	UNE-EN 16165:2022 Annex C	Wet		PTV ₅₇ ≥ 22
	Anexo Nacional A (ES)	Dry		PTV ₉₆ ≥ 56
Content		Heavy metals + lead/cadmium		NOT present
Dangerous substances		Carcinogenic, mutagenic or reprotoxic substances class 1A and 1B (candidate list)		NOT present
REACH				Compliant
Plasticizer		Phthalate free plasticizer except recycled content		
Recycled content		Minimum 25% Pre-Consumer Recycled PVC Content		SCS-RC-20324

INSTALLATION INSTRUCTIONS

RIGID CLICK VINYL



MAINTENANCE

